

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): A porous film of a ~~for use in an electronic device, in particular a solar cell, comprising:~~

~~said a~~ film having a front face and a back face, characterized in that the film including at least two layers, each layer having a first kind of particles of one average diameter or length and one layer having additionally a second kind of particles having a larger average diameter or length, said porous film has a gradient of light scattering strength extending from said front face to said back face, with the light scattering strength increasing towards said back face.

Claim 2 (Original): The porous film according to claim 1, ~~characterized in that~~ wherein said gradient of light scattering strength starts with zero light scattering at said front face.

Claim 3 (Canceled).

Claim 4 (Currently Amended): The porous film according to claim ~~[[3]]~~ 1, ~~characterized in that~~ wherein said ~~porous film comprises~~ at least two layers ~~is~~ three layers, each layer having a first kind of particles of one average diameter or length, and at least one layer having additionally at least a second kind of particles having a larger average diameter or length.

Claim 5 (Cancelled)

Claim 6 (Currently Amended): The porous film according to claim [[3]] 1, ~~characterized in that~~ wherein said particles have a shape selected from the group consisting of ~~comprising~~ rods, tubes, cylinders, cubes, parallelipeds, spheres, balls and ellipsoids.

Claim 7 (Currently Amended): The porous film according to claim [[3]] 1, ~~characterized in that~~ wherein said particles are selected from the group ~~comprising~~ consisting of semi-conducting material particles, metal particles and insulating particles.

Claim 8 (Currently Amended): The porous film according to claim [[3]] 1, ~~characterized in that~~ wherein the at least two layers/~~three layers/plurality of layers~~ have been applied subsequently.

Claim 9 (Currently Amended): The porous film according to claim 8, ~~characterized in that~~ wherein the at least two/~~three/plurality of~~ layers have been applied subsequently by a technique selected from the group ~~comprising~~ consisting of screen printing, doctor blading, drop casting, spin coating, sol gel process and lift-off techniques, and any combination of the aforementioned techniques.

Claim 10 (Currently Amended): The porous film according to claim [[3]] 1, ~~characterized in that~~ wherein the first kind of particles have an average diameter in the range of from 2 nm to 25 nm, preferably from 3 nm to 20 nm, or they have an average length of from 3 nm to 300 nm, preferably from 10 nm to 100 nm.

Claim 11 (Currently Amended): The porous film according to claim [[3]] 1, ~~characterized in that~~ wherein the second kind of particles have an average diameter or length

in the range of from 50 nm to 1 μ m, preferably from 100 nm to 500 nm, more preferably from 200 nm to 400 nm.

Claim 12 (Currently Amended): The porous film according to claim ~~[[3]]~~ 1, ~~characterized in that~~ wherein, in the layer(s) having additionally a second kind of particles, the ratio of the first kind of particles to the second kind of particles is in the range of from 10:1 to 1:1, preferably from 8:1 to 2:1.

Claim 13 (Currently Amended): The porous film according to claim 12, ~~characterized in that~~ wherein the ratio is a weight ratio.

Claim 14 (Currently Amended): The porous film according to claim 12, ~~characterized in that~~ wherein the ratio is a volume ratio.

Claim 15 (Previously Presented): The porous film according to claim 1, comprising a plurality of layers, each layer having a first kind of particles of one average diameter or length, and all but one layer having a second kind of particles, wherein in each of the layers having a second kind of particles, either (i) the average diameter or length of the second kind of particles is the same in each layer and the amount of the second kind of particles present in each layer varies from layer to layer, or (ii) the amount of the second kind of particles present in each layer is the same in each layer and the average diameter or length of the second kind of particles varies from layer to layer.

Claim 16 (Currently Amended): The porous film according to claim 15, ~~characterized in that~~ wherein, where the amount of the second kind of particles present in each layer varies

from layer to layer, it increases from layer to layer, and where the average diameter or length of the second kind of particles present in each layer varies from layer to layer, it increases from layer to layer.

Claim 17 (Currently Amended): The porous film according to claim 15, ~~characterized in that~~ wherein the one layer having only a first kind of particles is closer to said front face of said porous film than to said back face.

Claim 18 (Currently Amended): The porous film according to claim 17, ~~characterized in that~~ wherein said one layer having only a first kind of particle is adjacent to said front face.

Claim 19 (Previously Presented): Use of a porous film according to claim 1 in an electronic device, in particular a solar cell.

Claim 20 (Previously Presented): Electronic device comprising a porous film according to claim 1.

Claim 21 (Original): Electronic device according to claim 20, which is a solar cell.

Claim 22 (Original): Solar cell according to claim 21, further comprising a reflective back electrode.

Claim 23 (Previously Presented): Solar cell according to claim 21, further comprising a light confinement layer.

Claim 24 (Previously Presented): Solar cell according to claim 21, further comprising an electrolyte.

Claim 25 (Withdrawn): A method of forming a porous film having a gradient of light scattering strength across its thickness, comprising the steps:

- a) providing a first kind of particles having one average diameter or length,
- b) providing a second kind of particles,
- c) providing a substrate,
- d) applying onto said substrate a plurality of layers, each layer having said first kind of particles of one average diameter or length, and all but one layer having said second kind of particles, wherein in each of said layers having a second kind of particles, either

- (i) the average diameter or length of said second kind of particles is the same in each layer and the amount of said second kind of particles present in each layer varies from layer to layer,

or

- (ii) the amount of said second kind of particles present in each layer is the same in each layer and the average diameter or length of said second kind of particles varies from layer to layer.

Claim 26 (Withdrawn): A method according to claim 25, characterized in that, where the amount of said second kind of particles present in each layer varies from layer to layer, said amount increases from layer to layer, and, where said average diameter or length of said second kind of particles present in each layer varies from layer to layer, said average diameter or length increases from layer to layer.

Claim 27 (Withdrawn): The method according to claim 25, characterized in that steps a), b) and c) can be in any order.

Claim 28 (Withdrawn): The method according to claim 25, characterized in that the application of said plurality of layers occurs by a technique selected from the group comprising screen printing, doctor blading, drop casting, spin coating, sol gel process, and lift-off techniques, and any combination of the aforementioned techniques.

Claim 29 (Withdrawn): The method according to claim 25, characterized in that each layer is applied separately.

Claim 30 (Withdrawn): The method according to claim 29, characterized in that after application of a layer there is a drying step.

Claim 31 (Withdrawn): The method according to claim 25, characterized in that the porous film is sintered after all layers have been applied.

Claim 32 (Withdrawn): A porous film produced by the method according to claim 25.

Claim 33 (Withdrawn): Use of a porous film according to claim 32 in an electronic device, in particular a solar cell.

Claim 34 (Withdrawn): An electronic device comprising a porous film according to claim 32.